

POLYNIL® T34

Polyamide 66

Nilit Plastics

Message:

POLYNIL® T34 is an unreinforced semi dull Polyamide 66 (Nylon 66) for fiber spinning.
This 2.4 viscosity Polyamide 66 resin is FDA compliant.

General Information			
Uses	Fibers		
Agency Ratings	FDA Unspecified Rating		
Processing Method	Fiber (Spinning) Extrusion		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.14	g/cm ³	ISO 1183
Water Absorption			ISO 62
23°C, 24 hr	1.5	%	
Saturation, 23°C	8.5	%	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	225	°C	ISO 75-2/B
1.8 MPa, Unannealed	85.0	°C	ISO 75-2/A
Continuous Use Temperature ¹	85.0	°C	IEC 60216
Vicat Softening Temperature	240	°C	ISO 306/B
Melting Temperature	258	°C	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	28	%	ISO 4589-2
NOTE			

1. 20000 hr

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT