

Sumikon® PM-9625

Phenolic

Sumitomo Bakelite Co., Ltd.

Message:

Sumikon® PM-9625 is a phenolic (Phenolic) product. It can be processed by injection molding and is available in North America or Asia Pacific. Sumikon® PM-9625 applications include electrical/electronic applications and the automotive industry.

Features include:

flame retardant/rated flame

high strength

Heat resistance

General Information			
Features	High strength		
	Heat resistance, high		
Uses	Electrical components		
	Application in Automobile Field		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.92	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30	%	ASTM D955
Water Absorption (24 hr)	0.060	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	23000	MPa	ASTM D638
Tensile Strength	60.0	MPa	ASTM D638
Tensile Elongation (Break)	0.30	%	ASTM D638
Flexural Modulus (23°C)	18000	MPa	ASTM D790
Flexural Strength (23°C)	150	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	30	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	300	°C	ASTM D648
Linear thermal expansion coefficient			ASTM D696
Flow	1.2E-5	cm/cm/°C	ASTM D696
Lateral	1.5E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Dielectric Strength	10	kV/mm	ASTM D149
Arc Resistance	187	sec	ASTM D495

Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.00 mm)	V-0		UL 94
Additional Information			

Flexural Strength, ASTM D790, -40°C: 160 MPaFlexural Strength, ASTM D790, 150°C: 140 MPaFlexural Strength, ASTM D790, 200°C: 120 MPaFlexural Modulus, ASTM D790, -40°C: 20,000 MPaFlexural Modulus, ASTM D790, 150°C: 16,000 MPaFlexural Modulus, ASTM D790, 200°C: 15,000 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

