

TUFNYL® SST 35 BROWN

Polyamide 6

SRF Ltd.

Message:

Polyamide 6, Un-filled Super Tough, brown pigmented material for injection molding

General Information			
Features	Ultra High Toughness		
Appearance	Brown		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.5 to 2.0	%	Internal Method
Water Absorption (Equilibrium)	1.2	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	60		
R-Scale	100		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	45.0	MPa	ISO 527-2
Tensile Strain (Break)	100	%	ISO 527-2
Flexural Modulus	1700	MPa	ISO 178
Flexural Stress	75.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	147	J/m	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	125	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	°C	ISO 75-2/A
Melting Temperature	210	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	< 0.20	%	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	40.0 to 80.0	°C	
Injection Pressure	3.50 to 12.5	MPa	

Injection Rate

Fast

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

