

Multi-Flex® TPE D3804

Thermoplastic Elastomer

Multibase, A Dow Corning Company

Message:

Multi-Flex® TPE D3804 is a Thermoplastic Elastomer (TPE) product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Automotive.

General Information			
Features	Paintable		
Uses	Automotive Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.988	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.3	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 15 sec)	36		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	250	MPa	ISO 178
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (Break)	11.0	MPa	ISO 37
Tensile Elongation (Break)	570	%	ISO 37
Tear Strength	65	kN/m	ISO 34-1
Injection	Nominal Value	Unit	
Drying Temperature	65.6	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	204	°C	
Middle Temperature	210	°C	
Front Temperature	216	°C	
Nozzle Temperature	221	°C	
Processing (Melt) Temp	221	°C	
Mold Temperature	37.8 to 48.9	°C	
Injection Rate	Fast		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

