

VAMPSON L 5010

Polyphenylene Sulfide

Vamp Tech

Message:

Linear PPS, 50% glass fiber reinforced, UL 94 V0 at 3,2 mm, halogen and red phosphorus free, high chemical resistance and excellent operating temperature, good mechanicals properties.

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Features	Good Chemical Resistance		
	Halogen Free		
	Low (to None) Phosphorus Content		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.72	g/cm³	ASTM D792
Water Absorption (Saturation)	0.020	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	18000	MPa	ASTM D638
Tensile Strength (Yield)	160	MPa	ASTM D638
Tensile Elongation (Break)	1.5	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	5.0	kJ/m²	ISO 180/A
Unnotched Izod Impact Strength	25	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	265	°C	ASTM D648A
RTI Elec	200	°C	UL 746
RTI Imp	200	°C	UL 746
RTI Str	200	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating (3.20 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	130	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	320	°C	
Mold Temperature	140	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

