

Mytex® AN206L-02

Polypropylene

Mytex Polymers

Message:

Mytex® AN206L-02 is a Polypropylene product. It is available in North America. Typical application: Automotive.

General Information			
Uses	Automotive Exterior Parts		
	Automotive Under the Hood		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	Internal Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	31	g/10 min	Internal Method
Molding Shrinkage - Flow	1.2E-3	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	21.0	MPa	Internal Method
Tensile Elongation ² (Break)	150	%	Internal Method
Flexural Modulus ³	920	MPa	Internal Method
Flexural Strength ⁴	26.0	MPa	Internal Method
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			Internal Method
-30°C	49	J/m	
23°C	210	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	110	°C	Internal Method
Additional Information	Nominal Value	Unit	Test Method
DuPont Impact Strength			Internal Method
-30°C	17.0	J	
23°C	24.0	J	
NOTE			
1.	50 mm/min		
2.	50 mm/min		
3.	30 mm/min		
4.	30 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

