

Alcryn® 2060 NC

Melt Processable Rubber

Advanced Polymer Alloys

Message:

Alcryn® 2060 NC is a Melt Processable Rubber (MPR) material. It is available in Asia Pacific, Europe, or North America for blow molding, extrusion, injection molding, or vacuum forming.

Important attributes of Alcryn® 2060 NC are:

RoHS Compliant

Chemical Resistant

Eco-Friendly/Green

Fast Molding Cycle

Heat Resistant

Typical applications include:

Coating Applications

Engineering/Industrial Parts

Handles

Hose/Tubing

Wire & Cable

General Information	
UL YellowCard	E115006-219316
Features	Fast Molding Cycle
	General Purpose
	High Flow
	High Heat Resistance
	Noise Damping
	Oil Resistant
	Ozone Resistant
	Recyclable Material
	Vibration Damping
Uses	Cable Jacketing
	Coating Applications
	Fabric Coatings
	Flexible Grips
	Gaskets
	General Purpose
	Handles
	Hose
	Overmolding
	Profiles
	Seals
	Tubing
	Weatherstripping

Wire & Cable Applications

RoHS Compliance	RoHS Compliant
Appearance	Natural Color
Forms	Pellets
Processing Method	Blow Molding Extrusion Injection Molding Vacuum Forming

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm ³	ASTM D471, ISO 2781
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 1.90 mm, Compression Molded)	59		ASTM D2240, ISO 868
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (1000 Cycles, 1000 g, CS-17 Wheel)	5.00	mg	ASTM D1044
Torsion Modulus ¹			ASTM D1043
-20°C, 1.90 mm	4.80	MPa	
24°C, 1.90 mm	2.30	MPa	
Elastomers	Nominal Value	Unit	Test Method
Tensile Set ²	8	%	ASTM D412
Tensile Stress			
100% Strain, 1.90 mm ³	3.00	MPa	ASTM D412, ISO 37
100% Strain, 125°C, 1.90 mm ⁴	2.70	MPa	ASTM D573, ISO 188
Tensile Strength			
Yield, 1.90 mm ⁵	7.90	MPa	ASTM D412, ISO 37
Yield, 125°C, 1.90 mm ⁶	6.50	MPa	ASTM D573, ISO 188
Tensile Elongation			
Break, 125°C, 1.90 mm ⁷	340	%	ASTM D573, ISO 188
Break, 1.90 mm ⁸	420	%	ASTM D412, ISO 37
Tear Strength (1.90 mm)	28.0	kN/m	ASTM D624
Compression Set ⁹			ASTM D395B, ISO 815
24°C, 22 hr	13	%	
100°C, 22 hr	62	%	
Clash-Berg Modulus (-42°C)	68.9	MPa	ASTM D1043
Aging	Nominal Value	Unit	Test Method
Change in Durometer Hardness in Air ¹⁰ (Shore A, 125°C, 168 hr)	1.0		ASTM D573, ISO 188
Change in Volume ¹¹			
27°C, 168 hr, in Reference Fuel B	17	%	ASTM D471, ISO 1817
100°C, 168 hr, in ASTM Oil #1	-21	%	ASTM D471

100°C, 168 hr, in IRM 903 Oil	17	%	ASTM D471, ISO 1817
100°C, 168 hr, in Water	8.0	%	ASTM D471, ISO 1817
100°C, 168 hr, in ASTM #1 Oil	-21	%	ISO 1817
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-85.0	°C	ASTM D746, ISO 812
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (190°C, 300 sec ⁻¹)	350	Pa·s	ASTM D3835
Injection	Nominal Value	Unit	Test Method
Processing (Melt) Temp	177	°C	
NOTE			

1.	Compression Molded
2.	1.9 mm, Compression Molded
3.	Compression Molded
4.	7 days, Compression Molded
5.	Compression Molded
6.	7 days, Compression Molded
7.	7 days, Compression Molded
8.	Compression Molded
9.	Type I pellets, 12.7 mm diameter, plied up from 1.9 mm slabs
10.	1.9 mm, Compression Molded
11.	1.9 mm, Compression Molded

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT