

Tecomid® NB40 NL FY70

Polyamide 6
Eurotec Engineering Plastics

Message:
PA6, flame retardant - halogen (RoHS compliant), natural

General Information			
Additive	Flame retardancy		
Features	Flame retardancy		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	Natural color		
Processing Method	Injection molding		
Resin ID (ISO 1043)	PA6 FR(17)		
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Molding Shrinkage			Internal method
Vertical flow direction	1.1	%	Internal method
Flow direction	1.1	%	Internal method
Water Absorption (Equilibrium, 23°C, 50% RH)	2.7	%	ISO 62
Moisture Content		%	ISO 15512
Back Pressure	Low		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3250	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	70.0	MPa	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	6.0	kJ/m ²	ISO 180/1A
23°C	7.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	185	°C	ISO 75-2/B
1.8 MPa, not annealed	75.0	°C	ISO 75-2/A
Vicat Softening Temperature	200	°C	ISO 306/B
Melting Temperature ¹	223	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method

Flame Rating			UL 94
0.750 mm	V-2		UL 94
1.60 mm	V-2		UL 94
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (2.00 mm)	775	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 - 4.0	hr	
Hopper Temperature	60.0 - 80.0	°C	
Processing (Melt) Temp	230 - 250	°C	
Mold Temperature	40.0 - 90.0	°C	
Injection Rate	Moderate-Fast		
Holding Pressure	50.0 - 100	MPa	
Injection instructions			
Pre-drying is not necessary for materials in moisture proof closed bags.			
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT