

NEXUS Reprocessed Nylon 66 G33 RBK

Polyamide 66

Nexus Resin Group, LLC.

Message:

Glass filled, injection grade, nylon 66

Black Reprocessed Pellets

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Recycled Content	Yes		
Appearance	Black		
Forms	Pellets, Reprocessed		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.38	g/cm ³	ASTM D792
Ash Content	29 to 34	%	ASTM D5630
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	159	MPa	ASTM D638
Flexural Modulus	7580	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	260	°C	
1.8 MPa, Unannealed	232	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

