

EcoBlend® HCL7110NH

Polylactic Acid + PMMA

Shanghai KumhoSunny Plastics Co., Ltd.

Message:

HCL7110NH is a kind of appending 10%~20% biological base plastic environmental halogen free flame retardant PLA/PMMA resin.The flame retardant rate is 1.6mmV0.HCL7110NH is mainly used in ornament & housing of small appliance,etc.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogen Free		
	Renewable Resource Content		
Uses	Appliances		
	Housings		
UL File Number	E65424		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (240°C/5.0 kg)	21	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	59.0	MPa	ASTM D638
Tensile Elongation (Break)	12	%	ASTM D638
Flexural Modulus	2270	MPa	ASTM D790
Flexural Strength	77.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	540	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	84.0	°C	ASTM D648
Vicat Softening Temperature	85.0	°C	ASTM D1525 ¹
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Additional Information	Nominal Value	Unit	
Biobased Content	10 to 20	%	

CSA File No.	LS 66457	
Injection	Nominal Value	Unit
Drying Temperature	80.0 to 90.0	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	190 to 200	°C
Middle Temperature	210 to 220	°C
Front Temperature	220 to 230	°C
Nozzle Temperature	215 to 225	°C
Processing (Melt) Temp	220 to 230	°C
Mold Temperature	60.0 to 80.0	°C
Back Pressure	1.00 to 5.00	MPa
Screw Speed	30 to 60	rpm
NOTE		
1.	Rate B (120°C/h)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

