

AVP™ TLL40CP

Polycarbonate
SABIC Innovative Plastics

Message:

AVP™ TLL40CP is a Polycarbonate (PC) product. It can be processed by injection molding and is available in North America. Primary characteristic: high flow.

General Information			
Features	High Flow		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	38	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.18 mm)	58.6	MPa	ASTM D638
Tensile Elongation ² (Break, 3.18 mm)	75	%	ASTM D638
Flexural Modulus ³ (3.18 mm, 50.8 mm Span)	2410	MPa	ASTM D790
Flexural Strength ⁴ (3.18 mm, 50.8 mm Span)	93.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Reverse Notch Izod Impact (23°C, 3.18 mm)	2100	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.35 mm)	127	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Drying Time, Maximum	16	hr	
Rear Temperature	249 to 271	°C	
Middle Temperature	260 to 271	°C	
Front Temperature	271 to 288	°C	
Nozzle Temperature	266 to 282	°C	
Processing (Melt) Temp	271 to 288	°C	
Mold Temperature	71.1 to 93.3	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	40 to 70	rpm	
NOTE			
1.	5.1 mm/min		

2.	5.1 mm/min
3.	1.3 mm/min
4.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

