

GELOY™ HRA222F resin

Acrylonitrile Styrene Acrylate + PC

SABIC Innovative Plastics Europe

Message:

GELOY HRA222F is a multi-purpose, chlorine and bromine free flame retardant PC+ASA alloy for injection molding processes. F1 rating according UL746C. Use for exterior/interior electrical applications requiring UV resistance.

General Information			
UL YellowCard	E207780-100044615	E207780-100183331	
Features	Chlorine Free		
	Good UV resistance		
	Bromine-free		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Outdoor application		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	13.0	cm³/10min	ISO 1133
Molding Shrinkage - Flow ¹	0.40 - 0.60	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.60	%	ISO 62
Equilibrium, 23°C, 50% RH	0.20	%	ISO 62
Outdoor Suitability	f1		UL 746C
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ²	2590	MPa	ASTM D638
--	2520	MPa	ISO 527-2/1
Tensile Strength			
Yield ³	59.0	MPa	ASTM D638
Yield ⁴	63.0	MPa	ASTM D638
Yield	62.0	MPa	ISO 527-2/5
Yield	60.0	MPa	ISO 527-2/50
Fracture ⁵	66.0	MPa	ASTM D638
Fracture ⁶	56.0	MPa	ASTM D638
Fracture	51.0	MPa	ISO 527-2/5
Fracture	45.0	MPa	ISO 527-2/50
Tensile Elongation			

Yield ⁷	4.2	%	ASTM D638
Yield ⁸	4.3	%	ASTM D638
Yield	4.3	%	ISO 527-2/5
Yield	4.4	%	ISO 527-2/50
Fracture ⁹	> 100	%	ASTM D638
Fracture ¹⁰	> 100	%	ASTM D638
Fracture	> 50	%	ISO 527-2/5, ISO 527-2/50
Flexural Modulus ¹¹	2520	MPa	ISO 178
Flexural Stress	93.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ¹² (23°C)	15	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
0°C	290	J/m	ASTM D256
23°C	390	J/m	ASTM D256
-30°C ¹³	9.0	kJ/m ²	ISO 180/1A
0°C ¹⁴	12	kJ/m ²	ISO 180/1A
23°C ¹⁵	17	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹⁶			
0.45 MPa, unannealed, 100 mm span	99.0	°C	ISO 75-2/Be
1.8 MPa, unannealed, 100 mm span	88.0	°C	ISO 75-2/Ae
Vicat Softening Temperature			
--	111	°C	ISO 306/A50
--	102	°C	ISO 306/B50
--	104	°C	ISO 306/B120
Ball Pressure Test (75°C)	Pass		IEC 60695-10-2
Linear thermal expansion coefficient			
Flow: -30 to 80°C	6.9E-5	cm/cm/°C	ISO 11359-2
Horizontal: -30 to 80°C	7.1E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 80°C	7.5E-5	cm/cm/°C	ISO 11359-2
RTI Elec	90.0	°C	UL 746
RTI Imp	90.0	°C	UL 746
RTI	90.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 0		UL 746
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (2.00 mm)	V-0		UL 94
Oxygen Index	29	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	2.0 - 4.0	hr	

Suggested Max Moisture	0.020	%
Hopper Temperature	60.0 - 80.0	°C
Rear Temperature	200 - 230	°C
Middle Temperature	220 - 260	°C
Front Temperature	230 - 270	°C
Nozzle Temperature	220 - 260	°C
Processing (Melt) Temp	230 - 270	°C
Mold Temperature	50.0 - 70.0	°C

NOTE

1.	Tensile Bar
2.	5.0 mm/min
3.	Type 1, 5.0 mm/min
4.	Type 1, 50mm/min
5.	Type 1, 5.0 mm/min
6.	Type 1, 50mm/min
7.	Type 1, 5.0 mm/min
8.	Type 1, 50mm/min
9.	Type 1, 5.0 mm/min
10.	Type 1, 50mm/min
11.	2.0 mm/min
12.	80*10*4 sp=62mm
13.	80*10*4
14.	80*10*4
15.	80*10*4
16.	120*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT