

TECHNYL® A 218 V20 BLACK 21 N

Polyamide 66
Solvay Engineering Plastics

Message:
Polyamide PA66, reinforced with 20% of glass fibre, heat stabilized, for injection moulding.

General Information				
UL YellowCard		E44716-235569		
Filler / Reinforcement		Glass Fiber,20% Filler by Weight		
Additive		Heat Stabilizer		
Features		Heat Stabilized		
Uses		Automotive Applications		
		Containers		
Appearance		Black		
		Grey		
Processing Method		Injection Molding		
Multi-Point Data		Isothermal Stress vs. Strain (ISO 11403-1)		
		Secant Modulus vs. Strain (ISO 11403-1)		
		Viscosity vs. Shear Rate (ISO 11403-2)		
Part Marking Code (ISO 11469)		>PA66-GF20<		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.29	--	g/cm ³	ISO 1183/A
Water Absorption (23°C, 24 hr)	1.0	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	7400	5300	MPa	ISO 527-2/1A
Tensile Stress (Break)	145	100	MPa	ISO 527-2/1A
Tensile Strain (Break)	4.0	5.0	%	ISO 527-2/1A
Flexural Modulus	6400	4200	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	8.0	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	48	79	kJ/m ²	ISO 179/1eU
Notched Izod Impact Strength	7.0	13	kJ/m ²	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Melting Temperature	263	--	°C	ISO 11357-3

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	6.0E+14	1.0E+12	ohms	IEC 60093
Volume Resistivity	1.0E+15	1.0E+13	ohms·cm	IEC 60093
Electric Strength	32	28	kV/mm	IEC 60243-1
Relative Permittivity	3.70	4.00		IEC 60250
Dissipation Factor	0.010	0.11		IEC 60250
Comparative Tracking Index (Solution A)	450	350	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Glow Wire Flammability Index (1.60 mm)	650	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.60 mm)	650	--	°C	IEC 60695-2-13
Oxygen Index	23	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Suggested Max Moisture	0.20		%	
Rear Temperature	260 to 270		°C	
Middle Temperature	270 to 280		°C	
Front Temperature	280 to 290		°C	
Mold Temperature	60.0 to 80.0		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

