

LNP™ STAT-KON™ DX03571 compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP STAT-KON DX03571 is a compound based on Polycarbonate resin. Added features of this material include: Electrically Conductive.
Also known as: LNP* STAT-KON* Compound PDX-D-03571
Product reorder name: DX03571

General Information			
Features	Conductivity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2900	MPa	ASTM D638
Tensile Strength (Break)	60.7	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	2830	MPa	ASTM D790
Flexural Strength	96.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Unnotched Izod Impact (23°C)	1100	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	121	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 - 1.0E+4	ohms	ASTM D257
Volume Resistivity	1.0E+2 - 1.0E+4	ohms · cm	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 - 304	°C	
Middle Temperature	310 - 321	°C	
Front Temperature	321 - 332	°C	
Processing (Melt) Temp	304 - 327	°C	
Mold Temperature	82.2 - 110	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

