

Kepital® F30-63

Acetal (POM) Copolymer

Korea Engineering Plastics Co., Ltd

Message:

An easy-flowing speacial grade for injection molding of anti-static purpose. Also, it is good in noise reducing effect.

General Information			
UL YellowCard	E120354-220446		
Additive	Antistatic		
Features	Antistatic		
	Fatigue Resistant		
	Good Chemical Resistance		
	Good Creep Resistance		
	Good Moldability		
	Good Thermal Stability		
	Good Wear Resistance		
	Low Viscosity		
Uses	Audio Tapes		
	Automotive Applications		
	Electrical Parts		
	Electronic Data Processing		
	Industrial Parts		
	Machine/Mechanical Parts		
	Video Cassettes		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	27	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.00 mm)	2.0	%	ASTM D955
Water Absorption (Equilibrium, 23°C)	0.22	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	60.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	40	%	ASTM D638
Flexural Modulus (23°C)	2560	MPa	ASTM D790

Flexural Strength (Yield, 23°C)	83.0	MPa	ASTM D790
Shear Strength	55.0	MPa	ASTM D732
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	158	°C	
1.8 MPa, Unannealed	110	°C	
Melting Temperature	165	°C	
CLTE - Flow (20 to 80°C)	1.3E-4	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+11	ohms	ASTM D257
Volume Resistivity	1.0E+10	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

