

# ENFLEX S3145A

Thermoplastic Elastomer

ENPLAST Americas, a Ravago Group Company

Message:

45 Shore A TPE (Styrenic Block Copolymer based) available in both black and natural for injection molding and extrusion applications. This grade offers soft/tactile feel, adhesion (overmolding or co-extrusion) to Polypropylene and good sealing performance.

| General Information                       |                               |                   |             |
|-------------------------------------------|-------------------------------|-------------------|-------------|
| Features                                  | Low compressive deformability |                   |             |
|                                           | High elasticity               |                   |             |
|                                           | Solvent resistance            |                   |             |
|                                           | Good UV resistance            |                   |             |
|                                           | Recyclable materials          |                   |             |
|                                           | Workability, good             |                   |             |
|                                           | Good coloring                 |                   |             |
|                                           | Good adhesion                 |                   |             |
|                                           | Ozone resistance              |                   |             |
|                                           | alkali resistance             |                   |             |
|                                           | Alcohol resistance            |                   |             |
|                                           | acid resistance               |                   |             |
|                                           | Detergent resistance          |                   |             |
|                                           | Oil resistance                |                   |             |
|                                           | Soft                          |                   |             |
| Appearance                                | Black                         |                   |             |
|                                           | Natural color                 |                   |             |
| Processing Method                         | Extrusion                     |                   |             |
|                                           | Injection molding             |                   |             |
| Physical                                  | Nominal Value                 | Unit              | Test Method |
| Specific Gravity                          | 0.978                         | g/cm <sup>3</sup> | ASTM D792   |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 1.2                           | g/10 min          | ASTM D1238  |
| Hardness                                  | Nominal Value                 | Unit              | Test Method |
| Durometer Hardness                        |                               |                   | ASTM D2240  |
| Shaw A, 10 seconds, extruded              | 41                            |                   | ASTM D2240  |
| Shore A, 10 seconds, injection molding    | 45                            |                   | ASTM D2240  |
| Elastomers                                | Nominal Value                 | Unit              | Test Method |
| Tensile Stress (100% Strain)              | 0.614                         | MPa               | ASTM D412   |
| Tensile Strength (Break)                  | 4.31                          | MPa               | ASTM D412   |

|                            |      |      |            |
|----------------------------|------|------|------------|
| Tensile Elongation (Break) | 790  | %    | ASTM D412  |
| Tear Strength              | 21.0 | kN/m | ASTM D624  |
| Compression Set            |      |      | ASTM D395B |
| 23°C, 22 hr                | 20   | %    | ASTM D395B |
| 70°C, 22 hr                | 58   | %    | ASTM D395B |

| Thermal                     | Nominal Value | Unit | Test Method |
|-----------------------------|---------------|------|-------------|
| Brittleness Temperature     | -60.0         | °C   | ASTM D746   |
| Dynamic Service Temperature | 90            | °C   |             |

| Injection              | Nominal Value | Unit               |
|------------------------|---------------|--------------------|
| Drying Temperature     | 65.6 - 71.1   | °C                 |
| Drying Time            | 2.0 - 3.0     | hr                 |
| Rear Temperature       | 171 - 199     | °C                 |
| Middle Temperature     | 177 - 210     | °C                 |
| Front Temperature      | 191 - 221     | °C                 |
| Nozzle Temperature     | 199 - 229     | °C                 |
| Processing (Melt) Temp | 199 - 221     | °C                 |
| Mold Temperature       | 10.0 - 48.9   | °C                 |
| Injection Pressure     | 5.17 - 8.96   | MPa                |
| Injection Rate         | Fast          |                    |
| Screw Speed            | 50 - 200      | rpm                |
| Clamp Tonnage          | 2.8 - 4.8     | kN/cm <sup>2</sup> |
| Cushion                | 5.08 - 12.7   | mm                 |

#### Injection instructions

Holding Time: 5 to 7 Sec.

| Extrusion             | Nominal Value | Unit |
|-----------------------|---------------|------|
| Drying Temperature    | 65.6 - 71.1   | °C   |
| Drying Time           | 2.0 - 3.0     | hr   |
| Hopper Temperature    | 160 - 177     | °C   |
| Cylinder Zone 1 Temp. | 171 - 191     | °C   |
| Cylinder Zone 3 Temp. | 179 - 199     | °C   |
| Cylinder Zone 5 Temp. | 191 - 210     | °C   |
| Adapter Temperature   | 191 - 210     | °C   |
| Melt Temperature      | 191 - 199     | °C   |
| Die Temperature       | 191 - 210     | °C   |

#### Extrusion instructions

Screw: L/D 20:1 or greater (L/D 24:1 preferred) Cooling Water: 60 - 85°F (15-30°C) Screw Speed: 100 - 200 rpm Screen Pack: 20/40/60

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

