

Pibifor® K2 GF/30 NATURALE

Polybutylene Terephthalate

SO.F.TER. SPA

Message:

30% glass fiber reinforced, heat stabilized PBT grade

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm³	ASTM D792
Molding Shrinkage	0.60	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.40	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9700	MPa	ASTM D638
Tensile Strength (Break)	135	MPa	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	8000	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m²	ISO 179/1eA
Notched Izod Impact (23°C)	95	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	210	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	110	°C	
Drying Time	3.0	hr	
Rear Temperature	235	°C	
Middle Temperature	250	°C	
Front Temperature	260	°C	

Mold Temperature	70.0 to 100	°C
------------------	-------------	----

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

