

LARIPUR® LPR 6520

Thermoplastic Polyurethane Elastomer (Polyester)

COIM S.p.A.

Message:

LARIPUR® LPR 6520 is a thermoplastic polyurethane elastomer (polyester)(TPU-polyester) material. This product is available in North America, Latin America or Europe. The processing method is injection molding.

LARIPUR®The main features of LPR 6520 are:

Wear-resistant

Good tear strength

Good toughness

chemical resistance

General Information			
Features	Good tear strength		
	Good wear resistance		
	Good chemical resistance		
	Good wear resistance		
	Good toughness		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	65		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	360	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
50% strain	19.5	MPa	ASTM D412
100% strain	22.5	MPa	ASTM D412
300% strain	44.0	MPa	ASTM D412
Tensile Strength (Break)	64.7	MPa	ASTM D412
Tensile Elongation (Break)	420	%	ASTM D412
Tear Strength	190	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	150	°C	ASTM D1525
Additional Information			

Abrasion loss, DIN 53516: 40 mm³Tosion Test, ASTM D 1043, 20° C: 77 MPaTosion Test, ASTM D 1043, -20° C: 455 MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHEG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT