

Spartech Polycom SC5-4120H

Polypropylene Copolymer

Spartech Polycom

Message:

Spartech SC5-4120H is a medium viscosity PP copolymer resin for injection molding that features an unspecified amount of mica/calcium carbonate reinforcement. It is heat stabilized and lubricated for good processing characteristics.

Polypropylene is a versatile thermoplastic offering a useful balance of heat and chemical resistance, good mechanical and electrical properties and processing ease. PP is resistant to deformation at elevated temperatures.

A very versatile product for a wide variety of applications, Spartech SC5-4120H is recommended for industrial, transportation, sporting goods and electrical/electronic applications.

General Information			
Filler / Reinforcement	Calcium carbonate filler		
	Mica filler		
Additive	heat stabilizer		
	Lubricant		
Features	Copolymer		
	Workability, good		
	Good electrical performance		
	Good chemical resistance		
	Heat resistance, high		
	Thermal Stability		
	Thermal stability, good		
	Lubrication		
	Medium viscosity		
Uses	Electrical/Electronic Applications		
	Industrial application		
	Application in Automobile Field		
	Sporting goods		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	16	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method

Tensile Strength (Yield, 23°C)	24.1	MPa	ASTM D638
Flexural Modulus (23°C)	1380	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	64.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	90.6	°C	
Drying Time	1.0	hr	
Rear Temperature	216 - 227	°C	
Middle Temperature	221 - 232	°C	
Front Temperature	227 - 238	°C	
Nozzle Temperature	232 - 243	°C	
Processing (Melt) Temp	204 - 260	°C	
Mold Temperature	26.7 - 37.8	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

