

LEXAN™ 121SRM resin

Polycarbonate

SABIC Innovative Plastics Asia Pacific

Message:

Easy flow, impact modified, super release grade polycarbonate.

General Information			
UL YellowCard	E207780-526974		
Additive	Impact Modifier		
Features	Good Flow		
	Good Mold Release		
	Impact Modified		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	18	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Water Absorption (24 hr)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	65.0	MPa	ASTM D638
Tensile Elongation ² (Break)	140	%	ASTM D638
Flexural Modulus ³ (50.0 mm Span)	2300	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 50.0 mm Span)	97.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	800	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
1.8 MPa, Unannealed, 3.20 mm	124	°C	
1.8 MPa, Unannealed, 6.40 mm	134	°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	48	hr	
Processing (Melt) Temp	282 to 304	°C	
Mold Temperature	71.0 to 93.0	°C	
NOTE			
1.	Type I, 50 mm/min		
2.	Type I, 50 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

