# WanBlend® WHT-890E5

## Thermoplastic Polyurethane Elastomer (Polyether)

Wanhua Chemical Group Co., Ltd.

### Message:

WHT-190ET5 is polyester-based TPU/CB compound available in cylinder form that can solve a wide range of static decay, static shielding and electromagnetic shielding problems.

Applications:

Pipes, Belts, Component trays, Electronic component packaging, etc.

General Information			
Additive	Carbon Black		
Features	Electromagnetic Shielding (EMI)		
Uses	Belts/Belt Repair		
	Electrical/Electronic Applications		
	Packaging		
	Piping		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	92		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	7.00	MPa	
300% Strain	12.0	MPa	
Tensile Strength	22.0	MPa	ASTM D412
Tensile Elongation (Break)	470	%	ASTM D412
Tear Strength	88.0	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-40.0	°C	ASTM D3417
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+5	ohms	ASTM D257
Volume Resistivity	< 1.0E+5	ohms·cm	ASTM D257
Extrusion	Nominal Value	Unit	
Drying Temperature	95.0 to 100	°C	
Drying Time	2.0 to 3.0	hr	
Cylinder Zone 1 Temp.	190	°C	
Cylinder Zone 3 Temp.	190	°C	
Cylinder Zone 5 Temp.	195	°C	
Die Temperature	200	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

