

Kumho ABS 722P

Acrylonitrile Butadiene Styrene
Korea Kumho Petrochemical Co., Ltd.

Message:
Features: High rigidity, extrusion molding use
Applications: Tray for semi-conductor

General Information			
Features	High Rigidity		
Uses	Electrical Parts		
	Support Trays		
Processing Method	Extrusion Blow Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
200°C/21.6 kg	10	g/10 min	ASTM D1238
220°C/10.0 kg	6.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow	0.50 to 0.80	%	ASTM D955
--	0.50 to 0.80	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	110		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	50.0	MPa	ASTM D638
Yield	48.0	MPa	ISO 527-2
Tensile Elongation			
Yield	20	%	ASTM D638
Break	23	%	ISO 527-2
Flexural Modulus	2500	MPa	ASTM D790, ISO 178
Flexural Stress			
--	71.0	MPa	ISO 178
Yield	68.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	29	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.20 mm	320	J/m	ASTM D256
23°C, 6.40 mm	260	J/m	ASTM D256
23°C	28	kJ/m ²	ISO 180/1A

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	90.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	84.0	°C	ASTM D648
1.8 MPa, Unannealed	79.0	°C	ISO 75-2/A
Vicat Softening Temperature	94.0	°C	ISO 306/B50, ASTM D1525 1
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
NOTE			
1.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

