

Panlite® MN-3600HA

Polycarbonate

TEIJIN LIMITED

Message:

PC alloy grade

General Information			
UL YellowCard	E98529-253660	E244324-101599265	
Features	Bromine Free Flame Retardant		
Uses	Battery Cases Electrical Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (280°C/5.0 kg)	21.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.50 to 0.70	%	
Flow : 4.00 mm	0.50 to 0.70	%	
Water Absorption (23°C, 24 hr)	0.22	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2350	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	60.0	MPa	
Break	60.0	MPa	
Tensile Strain			ISO 527-2/50
Yield	8.0	%	
Break	100	%	
Flexural Modulus ¹	2300	MPa	ISO 178
Flexural Stress ²	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	60	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	126	°C	ISO 75-2/B

1.8 MPa, Unannealed	113	°C	ISO 75-2/A
CLTE			ISO 11359-2
Flow	7.0E-5	cm/cm/°C	
Transverse	7.0E-5	cm/cm/°C	
RTI Elec (1.50 mm)	95.0	°C	UL 746
RTI Imp (1.50 mm)	95.0	°C	UL 746
RTI Str (1.50 mm)	95.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.450 mm	HB		
1.00 mm	V-1		
1.50 mm	V-0		
2.00 mm	5VB		
3.00 mm	5VA		
Glow Wire Flammability Index			IEC 60695-2-12
1.00 mm	960	°C	
1.50 mm	930	°C	
2.00 mm	960	°C	
3.00 mm	930	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
1.00 mm	875	°C	
1.50 mm	825	°C	
2.00 mm	825	°C	
3.00 mm	825	°C	
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

