

POCAN® DP 1105 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, non-reinforced, injection molding, Extrusion, improved flowability

General Information			
Features	Good liquidity		
Agency Ratings	EC 1907/2006 (REACH)		
Forms	Particle		
Processing Method	Extrusion		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.31	g/cm ³	ISO 1183
Apparent Density	0.80	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (250°C/1.2 kg)	42.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction: 250°C, 2.00mm ¹	2.4	%	ISO 294-4
Vertical flow direction: 120°C, 2 hours, 2.00mm ²	0.10	%	ISO 294-4
Flow direction: 250°C, 2.00mm ³	2.2	%	ISO 294-4
Flow direction: 120°C, 2 hours, 2.00mm ⁴	0.30	%	ISO 294-4
Water Absorption			ISO 62
Saturated, 23°C	0.50	%	ISO 62
Equilibrium, 23°C, 50% RH	0.20	%	ISO 62

Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	145	MPa	ISO 2039-1

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2850	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C)	65.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C)	9.0	%	ISO 527-2/50
Nominal Tensile Strain at Break (23°C)	10	%	ISO 527-2/50
Flexural Modulus ⁵ (23°C)	2750	MPa	ISO 178/A
Flexural Stress ⁶			
3.5% strain	80.0	MPa	ISO 178/A
23°C	90.0	MPa	ISO 178
Flexural Strain at Flexural Strength ⁷ (23°C)	6.5	%	
ISO Shortname	PBT, GHMR, 07-030		ISO 7792
Residual Moisture Content	0.0 - 0.020	%	Karl Fisher

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	110	kJ/m ²	ISO 179/1eU
23°C	140	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	70	kJ/m ²	ISO 180/1U
23°C	80	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	160	°C	ISO 75-2/B
1.8 MPa, not annealed	65.0	°C	ISO 75-2/A
Vicat Softening Temperature	185	°C	ISO 306/B120
Melting Temperature ⁸	223	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	1.0E-4	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.0E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+17	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+16	ohms · cm	IEC 60093
Dielectric Strength (23°C, 1.00 mm)	30	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	3.40		IEC 60250
23°C, 1 MHz	3.20		IEC 60250
Dissipation Factor			IEC 60250
23°C, 100 Hz	1.4E-3		IEC 60250
23°C, 1 MHz	0.022		IEC 60250
Comparative Tracking Index (Solution A)	350	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	HB		UL 94
1.60 mm	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	700	°C	IEC 60695-2-12
Oxygen Index ⁹	25	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 - 8.0	hr	

Processing (Melt) Temp	250 - 260	°C
Mold Temperature	80.0 - 100	°C
NOTE		
1.	60x60x2; WZ 80°C; 600 Bar	
2.	60x60x2	
3.	60x60x2; WZ 80°C; 600 Bar	
4.	60x60x2	
5.	2.0 mm/min	
6.	2.0 mm/min	
7.	Pull Rate: 2 mm/min; 50% RH	
8.	10°C/min	
9.	Procedure A	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT