

DURACON® CH-10

Acetal (POM) Copolymer

Polyplastics Co., Ltd.

Message:

DURACON®CH-10 is a polyoxymethylene (POM) copolymer product, which contains a 10% carbon fiber reinforced material. It can be processed by injection molding and is available in North America, Europe or the Asia-Pacific region.

Features include:

flame retardant/rated flame

Conductivity

Wear-resistant

General Information			
UL YellowCard	E45034-235709		
Filler / Reinforcement	Carbon fiber reinforced material, 10% filler by weight		
Features	Conductivity		
	Good wear resistance		
UL File Number	E45034		
Forms	Particle		
Processing Method	Injection molding		
Part Marking Code (ISO 11469)	>POM-CF10		
Physical	Nominal Value	Unit	Test Method
Density	1.44	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	3.30	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	95		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8800	MPa	ISO 527-2
Tensile Stress	116	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	7500	MPa	ISO 178
Flexural Stress	170	MPa	ISO 178
Coefficient of Friction			JIS K7218
Dynamic ¹	0.37		JIS K7218
With steel-dynamic ²	0.28		JIS K7218
Wear Factor			JIS K7218
0.49 MPa, 0.30 m/sec ³	10	10 ⁻⁸ mm ³ /N·m	JIS K7218
0.060 MPa, 0.15 m/sec ⁴	200	10 ⁻⁸ mm ³ /N·m	JIS K7218
0.49 MPa, 0.30 m/sec ⁵	500	10 ⁻⁸ mm ³ /N·m	JIS K7218

0.060 MPa, 0.15 m/sec ⁶	10000	10 ⁻⁸ mm ³ /N·m	JIS K7218
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	163	°C	ISO 75-2/A
Linear thermal expansion coefficient			Internal method
Flow: 23 to 55°C	2.0E-5	cm/cm/°C	Internal method
Lateral: 23 to 55°C	9.0E-5	cm/cm/°C	Internal method
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+3	ohms	IEC 60093
Volume Resistivity	2.0E+4	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value		
Color Number	CD3501		
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	3.0 - 4.0	hr	
Processing (Melt) Temp	190 - 210	°C	
Mold Temperature	60.0 - 80.0	°C	
Injection Pressure	49.0 - 98.0	MPa	
Screw Speed	100 - 150	rpm	
Injection instructions			
Injection speed: 5-50 mm/sInjection Holding pressure: Gate sealing time + alphaCooling: Plasticizing time or ejection capable time			
NOTE			
1.	vs. M90-44, 0.06 MPa, 15 cm/s		
2.	0.49 MPa, 30 cm/s		
3.	vs C-Steel, Steel Side		
4.	vs M90-44, Material Side		
5.	vs C-Steel, Material Side		
6.	vs M90-44, M90-44 Side		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT