

Durethan® BKV 15 H3.0 DUS008 000000

Polyamide 6

LANXESS GmbH

Message:

PA 6, 15 % glass fibers, injection molding, heat-aging stabilized

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 15% filler by weight		
Additive		heat stabilizer		
Features		Good heat aging resistance		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.23	--	g/cm ³	ISO 1183
Molding Shrinkage				
Vertical flow direction: 280°C, 3.00mm ¹	0.60	--	%	ISO 2577
Vertical flow direction: 120°C, 2 hours, 3.00mm ²	0.15	--	%	ISO 294-4
Flow direction: 280°C, 3.00mm ³	0.35	--	%	ISO 2577
Flow direction: 120°C, 2 hours, 3.00mm ⁴	0.15	--	%	ISO 2577
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	6500	3100	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	130	65.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	12	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	5500	3100	MPa	ISO 178/A
Flexural Stress ⁶				
3.5% strain	180	80.0	MPa	ISO 178/A
23°C	205	110	MPa	ISO 178
Flexural Strain at Flexural Strength ⁷ (23°C)	5.3	8.0	%	
ISO Shortname	PA6, GHR, 14-070, GF15	--		ISO 1874
Residual Moisture Content	0.030 - 0.12		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	45	45	kJ/m ²	ISO 179/1eU
23°C	50	100	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	< 10	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U

-30°C	40	40	kJ/m²	ISO 180/1U
23°C	45	85	kJ/m²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	215	--	°C	ISO 75-2/B
1.8 MPa, not annealed	195	--	°C	ISO 75-2/A
Melting Temperature ⁸	220	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	3.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.0E-4	--	cm/cm/°C	ISO 11359-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	
Processing (Melt) Temp	260 - 290		°C	
Mold Temperature	80.0 - 100		°C	
NOTE				
1.	150x150x3; MT 80°C; 500 Bar			
2.	150x150x3			
3.	150x150x3; MT 80°C; 500 Bar			
4.	150x150x3			
5.	2.0 mm/min			
6.	2.0 mm/min			
7.	Pull Rate: 2 mm/min; 50% RH			
8.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT