

Monprene® WR-12263

Thermoplastic Elastomer

Teknor Apex Company

Message:

Monprene WR-12263 is a general purpose thermoplastic elastomer designed for a variety of consumer product applications requiring a soft, rubber-like feel. Monprene WR-12263 is a medium hardness grade, suitable for injection molding and extrusion.

General Information			
Features	Low Specific Gravity		
	Without Fillers		
	Low density		
	smoothness		
	Medium liquidity		
	Lubrication		
	Medium hardness		
Uses	Safety equipment		
	Handle		
	Packaging		
	Kitchen utensils		
	Pipe fittings		
	Sporting goods		
	Stationery		
Appearance	Consumer goods application field		
Forms	Natural color		
Processing Method	Particle		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.888	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 second, injection molding	60		ASTM D2240
Shore A, 5 seconds, injection molding	58		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
Transverse flow: 100% strain ¹	1.77	MPa	ASTM D412

Flow: 100% strain ²	2.37	MPa	ASTM D412
Transverse flow: 300% strain ³	2.63	MPa	ASTM D412
Flow: 300% strain ⁴	3.24	MPa	ASTM D412
Tensile Strength ⁵			ASTM D412
Transverse flow: Fracture	9.49	MPa	ASTM D412
Flow: Fracture	4.45	MPa	ASTM D412
Tensile Elongation ⁶			ASTM D412
Transverse flow: Fracture	800	%	ASTM D412
Flow: Fracture	530	%	ASTM D412
Tear Strength ⁷			ASTM D624
Transverse flow	27.8	kN/m	ASTM D624
Flow	25.4	kN/m	ASTM D624
Compression Set ⁸			ASTM D395B
23°C, 22 hr	22	%	ASTM D395B
70°C, 22 hr	55	%	ASTM D395B
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -60.0	°C	ASTM D746
Additional Information			
油脂膨胀,50 C = 6%			
Injection	Nominal Value	Unit	
Rear Temperature	182 - 232	°C	
Middle Temperature	188 - 238	°C	
Front Temperature	193 - 243	°C	
Nozzle Temperature	199 - 249	°C	
Processing (Melt) Temp	199 - 249	°C	
Mold Temperature	35.0 - 48.9	°C	
Injection Pressure	1.38 - 5.52	MPa	
Injection Rate	Fast		
Back Pressure	0.172 - 0.689	MPa	
Screw Speed	50 - 100	rpm	
Cushion	3.81 - 25.4	mm	
Injection instructions			
无需干燥.但如果湿度过大,则将粒料在150°F (65°C)的温度下干燥2-4小时.			
Extrusion	Nominal Value	Unit	
Cylinder Zone 1 Temp.	182 - 232	°C	
Cylinder Zone 2 Temp.	188 - 238	°C	
Cylinder Zone 3 Temp.	193 - 243	°C	
Cylinder Zone 5 Temp.	199 - 249	°C	
Die Temperature	199 - 249	°C	
Extrusion instructions			
螺杆转速30 - 100 rpm			
NOTE			

1.	Mouth die C, 510mm/min
2.	Mouth die C, 510mm/min
3.	C mold, 510mm/min
4.	C mold, 510mm/min
5.	C mold, 510mm/min
6.	Mouth die C, 510mm/min
7.	C mold, 510mm/min
8.	Type 1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

