

CYCOLAC™ INP572 resin

Acrylonitrile Butadiene Styrene + SAN

SABIC Innovative Plastics

Message:

High molecular weight SAN, functions as a carrier resin for color concentrates. Can be used as compounding additives for polymer blends. Can be blended with high rubber graft modifier resins to produce customized ABS properties. Suitable for direct weather exposure. Provides excellent melt strength for extrusion, blow molding, or thermoforming applications.

General Information			
Features	Good Weather Resistance		
	High Molecular Weight		
Uses	Blending		
	Compounding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
230°C/3.8 kg	5.9	g/10 min	ASTM D1238
220°C/10.0 kg	16	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus			
50.0 mm Span ¹	3900	MPa	ASTM D790
-- ²	3460	MPa	ISO 178
Flexural Stress			
--	92.0	MPa	ISO 178
Yield, 50.0 mm Span ³	134	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	1.4	kJ/m ²	ISO 179/2U
Notched Izod Impact			
23°C	46	J/m	ASTM D256
-30°C ⁴	2.0	kJ/m ²	ISO 180/1A
23°C ⁵	3.2	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	95.9	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	85.4	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁶	88.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	103	°C	ISO 306/B50
--	105	°C	ISO 306/B120

NOTE	
1.	1.3 mm/min
2.	2.0 mm/min
3.	1.3 mm/min
4.	80*10*4
5.	80*10*4
6.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

