

Forprene® 6NM001A70

Thermoplastic Vulcanizate

SO.F.TER. SPA

Message:

Forprene® 6NM001A70 is a Thermoplastic Vulcanizate (TPV) material. It is available in Europe, Latin America, or North America for injection molding.

Primary attribute of Forprene® 6NM001A70: REACH Compliant.

Typical applications include:

Appliances

Automotive

Industrial Applications

Sealing Applications

General Information			
Uses	Appliances		
	Automotive Applications		
	Industrial Applications		
	Seals		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.960	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	72		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Set	18	%	ASTM D412
Tensile Stress ¹ (100% Strain)	2.60	MPa	ASTM D412
Tensile Strength ²	6.50	MPa	ASTM D412
Tensile Elongation ³ (Break)	520	%	ASTM D412
Tear Strength ⁴	29.0	kN/m	ASTM D624
Compression Set ⁵ (70°C, 22 hr)	36	%	ASTM D395B
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Rear Temperature	160	°C	
Middle Temperature	170	°C	
Front Temperature	180	°C	
Nozzle Temperature	185	°C	
Mold Temperature	20.0 to 40.0	°C	
NOTE			
1.	Die C		

2.	Die C
3.	Die C
4.	Die C
5.	Type 1

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

