

# RTP 3401-3

Liquid Crystal Polymer

RTP Company

Message:

Glass Fiber

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	11400	MPa	ASTM D638
Tensile Strength	162	MPa	ASTM D638
Tensile Elongation (Yield)	2.0 - 3.0	%	ASTM D638
Flexural Modulus	10000	MPa	ASTM D790
Flexural Strength	186	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	160	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	530	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	266	°C	ASTM D648
Additional Information	Nominal Value	Unit	
Primary Additive	10	%	
Injection	Nominal Value	Unit	
Drying Temperature	149	°C	
Drying Time	8.0	hr	
Dew Point	-28.9	°C	
Processing (Melt) Temp	332 - 366	°C	
Mold Temperature	65.6 - 121	°C	
Injection Pressure	82.7 - 124	MPa	
Injection instructions			

The key to successfully molding this material is to start mold open cycles as soon as the screw reaches its retracted position.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

