

HIDEN® P502

High Density Polyethylene

YUHWHA Korea Petrochemical Ind. Co., Ltd.

Message:

HIDEN® P502 is a High Density Polyethylene material. It is available in Asia Pacific.

Important attributes of HIDEN® P502 are:

Creep Resistant

Good Flexibility

Typical application of HIDEN® P502: Plumbing/Piping/Potable Water

General Information			
Features	Good Creep Resistance		
	Good Flexibility		
Uses	Piping		
Agency Ratings	PPI PE-80		
Appearance	Natural Color		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.939	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.15	g/10 min	ASTM D1238
Water Absorption (Equilibrium)	< 0.010	%	ASTM D570
Environmental Stress-Cracking Resistance ¹ (Condition B)	> 5000	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	58		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	19.1	MPa	ASTM D638
Tensile Elongation (Break)	> 600	%	ASTM D638
Flexural Modulus	588	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	> 490	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	57.0	°C	ASTM D648
Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	120	°C	ASTM D1525
Peak Melting Temperature	130	°C	ASTM D3418
CLTE - Flow	1.5E-4	cm/cm/°C	ASTM D696
Oxidation Induction Time (200°C)	> 40	min	ASTM D3895
NOTE			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

