

Rilsan® BZM 30 Noir TL

Polyamide 11

Arkema

Message:

Rilsan ® BZM 30 Noir TL is a fibreglass reinforced polyamide 11 produced from a renewable source. This black coloured grade is designed for injection.

MAIN APPLICATIONS

Quick connectors.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Features	Renewable Resource Content		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.25	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (235°C/5.0 kg)	7.00	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore D	78		
Shore D, 15 sec	74		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6900	MPa	ISO 527-2
Tensile Stress (Break)	110	MPa	ISO 527-2
Tensile Strain (Break)	6.0	%	ISO 527-2
Flexural Modulus	5180	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-30°C	11	kJ/m ²	
23°C	20	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	83	kJ/m ²	
23°C	74	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	189	°C	ISO 11357-3
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
ISO Shortname	PA11, MHLR, 18-070, GF 30		ISO 1874
Renewable Carbon Content	> 95	%	ASTM D6866
Injection	Nominal Value	Unit	

Drying Temperature	80.0 to 90.0	°C
Drying Time	4.0 to 6.0	hr
Processing (Melt) Temp	250 to 290	°C
Mold Temperature	40.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

