

FRblend® PP-1306

Polypropylene

Colour Image Plastic Compound Sdn. Bhd. (CIPC)

Message:

FRblend® PP-1306 is an easy flow, mineral filled, flame retardant polypropylene compound. The flame retardant system is base on halogenated hydrocarbon compounds.

General Information			
UL YellowCard	E316349-100578005		
Filler / Reinforcement	Mineral		
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Flow		
	Good Impact Resistance		
	Halogenated		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.60 to 1.0	%	ASTM D955
Water Absorption (24 hr)	0.030	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2750	MPa	ASTM D638
Tensile Strength	25.0	MPa	ASTM D638
Tensile Elongation (Break)	14	%	ASTM D638
Flexural Modulus	2630	MPa	ASTM D790
Flexural Strength	41.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	40	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 4.00 mm)	120	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (1.60 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	

Drying Temperature	60.0 to 80.0	°C
Drying Time	2.0 to 4.0	hr
Middle Temperature	180 to 190	°C
Front Temperature	190 to 200	°C
Nozzle Temperature	210 to 220	°C
Mold Temperature	30.0 to 60.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

