

XYLEX™ X8303CL resin

Polycarbonate + Polyester
SABIC Innovative Plastics Europe

Message:

PC+ POLYESTER, Transparent, Low processing Temperature, High flow with excellent impact, UV stabilized, OQ quality. For In Mold Decoration /Labeling.

General Information			
UL YellowCard	E45329-100113033		
Additive	UV Stabilizer		
Features	Good Processability		
	High Flow		
	High Impact Resistance		
Uses	Decorative Parts		
	Labels		
RoHS Compliance	RoHS Compliant		
Appearance	Clear/Transparent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (265°C/2.16 kg)	30	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (265°C/2.16 kg)	27.5	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.40 to 0.80	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.50	%	
Equilibrium, 23°C, 50% RH	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1680	MPa	ASTM D638
--	1690	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	46.0	MPa	ASTM D638
Yield	48.0	MPa	ISO 527-2/50
Break ³	44.0	MPa	ASTM D638
Break	43.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	5.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/50

Break ⁵	140	%	ASTM D638
Break	140	%	ISO 527-2/50
Flexural Modulus			
50.0 mm Span ⁶	1620	MPa	ASTM D790
-- ⁷	1720	MPa	ISO 178
Flexural Stress			
--	72.0	MPa	ISO 178
Yield, 50.0 mm Span ⁸	72.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	14	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	100	J/m	ASTM D256
23°C	1000	J/m	ASTM D256
-30°C ¹⁰	9.0	kJ/m ²	ISO 180/1A
23°C ¹¹	20	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	65.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	92.0	°C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	80.0	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹²	90.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	98.0	°C	ASTM D1525 ¹³
--	100	°C	ISO 306/B50, ISO 306/B120
CLTE			
Flow : -40 to 40°C	9.0E-5	cm/cm/°C	ASTM E831
Flow : 23 to 60°C	9.2E-5	cm/cm/°C	ISO 11359-2
Transverse : -40 to 40°C	9.0E-5	cm/cm/°C	ASTM E831
Transverse : 23 to 60°C	9.8E-5	cm/cm/°C	ISO 11359-2
Optical	Nominal Value	Unit	Test Method
Transmittance (2540 µm)	88.0	%	ASTM D1003
Haze (2540 µm)	2.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	3.0 to 5.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	235 to 255	°C	
Middle Temperature	235 to 265	°C	
Front Temperature	240 to 270	°C	
Nozzle Temperature	240 to 270	°C	
Processing (Melt) Temp	240 to 270	°C	

Mold Temperature	50.0 to 70.0	°C
Screw Speed	20 to 100	rpm
NOTE		
1.	5.0 mm/min	
2.	Type I, 50 mm/min	
3.	Type I, 50 mm/min	
4.	Type I, 50 mm/min	
5.	Type I, 50 mm/min	
6.	1.3 mm/min	
7.	2.0 mm/min	
8.	1.3 mm/min	
9.	80*10*4 sp=62mm	
10.	80*10*4	
11.	80*10*4	
12.	80*10*4 mm	
13.	Rate B (120°C/h), Loading 2 (50 N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

