

# RTP EMI 2561 FR

Polycarbonate + ABS

RTP Company

Message:

Stainless Steel Fiber - Electrically Conductive - EMI/RFI/ESD Protection - Flame Retardant

| General Information                |                                             |                   |                  |
|------------------------------------|---------------------------------------------|-------------------|------------------|
| UL YellowCard                      | E84658-251326                               |                   |                  |
| Filler / Reinforcement             | Stainless steel fiber, 10% filler by weight |                   |                  |
| Features                           | Conductivity                                |                   |                  |
|                                    | Electromagnetic shielding (EMI)             |                   |                  |
|                                    | Electrostatic discharge protection          |                   |                  |
|                                    | Radio frequency shielding (RFI)             |                   |                  |
| RoHS Compliance                    | Contact manufacturer                        |                   |                  |
| Processing Method                  | Injection molding                           |                   |                  |
| Physical                           | Nominal Value                               | Unit              | Test Method      |
| Specific Gravity                   | 1.39                                        | g/cm <sup>3</sup> | ASTM D792        |
| Molding Shrinkage - Flow (3.20 mm) | 0.40 - 0.60                                 | %                 | ASTM D955        |
| Moisture Content                   | 0.020                                       | %                 |                  |
| Static Decay <sup>1</sup>          |                                             | sec               | FTMS 101C 4046.1 |
| Primary Additive                   | 10                                          | %                 |                  |
| Mechanical                         | Nominal Value                               | Unit              | Test Method      |
| Tensile Modulus                    | 2760                                        | MPa               | ASTM D638        |
| Tensile Strength                   | 62.1                                        | MPa               | ASTM D638        |
| Tensile Elongation (Yield)         | 3.0 - 5.0                                   | %                 | ASTM D638        |
| Flexural Modulus                   | 3100                                        | MPa               | ASTM D790        |
| Flexural Strength                  | 110                                         | MPa               | ASTM D790        |
| Impact                             | Nominal Value                               | Unit              | Test Method      |
| Notched Izod Impact (3.20 mm)      | 43                                          | J/m               | ASTM D256        |
| Unnotched Izod Impact (3.20 mm)    | 320                                         | J/m               | ASTM D4812       |
| Electrical                         | Nominal Value                               | Unit              | Test Method      |
| Surface Resistivity                |                                             |                   |                  |
| --                                 | < 1.0E+5                                    | ohms              | ASTM D257        |
| --                                 | < 1.0E+4                                    | ohms              | ESD STM11.11     |
| Volume Resistivity                 | < 1.0E+2                                    | ohms · cm         | ASTM D257        |
| Flammability                       | Nominal Value                               | Unit              | Test Method      |
| Flame Rating (1.50 mm)             | V-0                                         |                   | UL 94            |
| Injection                          | Nominal Value                               | Unit              |                  |
| Drying Temperature                 | 93.3                                        | °C                |                  |

|                        |             |     |
|------------------------|-------------|-----|
| Drying Time            | 4.0         | hr  |
| Dew Point              | -28.9       | °C  |
| Processing (Melt) Temp | 243 - 274   | °C  |
| Mold Temperature       | 51.7 - 93.3 | °C  |
| Injection Pressure     | 68.9 - 103  | MPa |

#### Injection instructions

Use a reverse barrel profile. Remove hopper magnets. Allow 4 - 5 shots to properly disperse the conductive fibers. The surface finish should have a silver streaking appearance, not clumps. Remove hopper magnets. Desiccant Type Dryer Required.

#### NOTE

1. MIL-PRF-81705D, 5kV to 50 V, 12% RH

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

