

Kumho ABS 710

Acrylonitrile Butadiene Styrene
Korea Kumho Petrochemical Co., Ltd.

Message:

Features: General plating
Applications: Automobile parts, Cosmetics cases, Refrigerator knobs, Various Knobs

General Information			
UL YellowCard	E65424-247677		
Uses	Automotive Applications		
	Household Goods		
RoHS Compliance	RoHS Compliant		
UL File Number	E65424		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
200°C/21.6 kg	40	g/10 min	ASTM D1238
220°C/10.0 kg	28	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			
Flow	0.50 to 0.80	%	ASTM D955
--	0.50 to 0.80	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	102		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	40.2	MPa	ASTM D638
Yield	39.0	MPa	ISO 527-2
Tensile Elongation			
Yield	25	%	ASTM D638
Break	25	%	ISO 527-2
Flexural Modulus			
--	1960	MPa	ASTM D790
--	2100	MPa	ISO 178
Flexural Stress			
--	62.0	MPa	ISO 178
Yield	58.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	34	kJ/m ²	ISO 179/1eA
Notched Izod Impact			

23°C, 3.20 mm	350	J/m	ASTM D256
23°C, 6.40 mm	310	J/m	ASTM D256
23°C	33	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	89.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	83.0	°C	ASTM D648
1.8 MPa, Unannealed	78.0	°C	ISO 75-2/A
Vicat Softening Temperature	93.0	°C	ISO 306/B50, ASTM D1525 1
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
NOTE			

1. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

