

UBE Nylon 1013NW8

Polyamide 6
UBE Industries, Ltd.

Message:
Low viscosity, short cycle (Injection)

General Information			
Features	Fast Molding Cycle		
	Low Viscosity		
Forms	Pellets		
Processing Method	Injection Molding		
Part Marking Code	>PA6<		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	1.3	%	
Flow	1.2	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	2.5	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3200	MPa	ISO 527-2
Tensile Stress (Yield)	85.0	MPa	ISO 527-2
Tensile Strain (Break)	20	%	ISO 527-2
Flexural Modulus	2700	MPa	ISO 178
Flexural Stress	110	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	5.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	175	°C	ISO 75-2/B
1.8 MPa, Unannealed	65.0	°C	ISO 75-2/A
CLTE - Flow	8.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Electric Strength	20	kV/mm	IEC 60243-1
Relative Permittivity	3.50		IEC 60250
Arc Resistance	119	sec	ASTM D495
Comparative Tracking Index (CTI)	PLC 0		UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.660 mm)	V-2		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

