

HAIPLEN H10 T8 HT

Polypropylene Homopolymer

Taro Plast S.p.A.

Message:

Polypropylene homopolymer 40% talcum filled, low flow, high stiffness and heat ageing stability.

General Information			
Filler / Reinforcement	Talc filler, 40% filler by weight		
Features	Rigidity, high		
	Homopolymer		
	Good heat aging resistance		
	Low liquidity		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.22 - 1.25	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ISO 1133
Molding Shrinkage			Internal method
Vertical flow direction	0.90	%	Internal method
Flow direction	0.90	%	Internal method
Water Absorption (23°C, 24 hr)	0.050	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	35.0	MPa	ISO 527-2/50
Tensile Strain (Break)	22	%	ISO 527-2/50
Flexural Modulus ¹	3800	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	25	J/m	ASTM D256
Aging	Nominal Value	Unit	Test Method
Aging Resistance ²	150	°C	Internal method
Reinforcement Content ³ (600°C)	40	%	ISO 3451
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	85.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	155	°C	ISO 306/A50
--	95.0	°C	ISO 306/B50
CLTE - Flow	6.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	

Processing (Melt) Temp	190 - 220	°C
Mold Temperature	50.0 - 70.0	°C
Injection Rate	Moderate	
Injection instructions		
Pre-heat Temperature: 80 to 100°CPre-heat Time: 1 hr		
NOTE		
1.	1.0 mm/min	
2.	700 hr	
3.	1 hr	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT