

Cellophane™ 360XSB

Regenerated Cellulose

Innovia Films Ltd.

Message:

Coated Barrier Films for Packageing Applications
White, general purpose 2 side PVdC coated, heat sealable, high barrier films.
Literature reference: A310

General Information			
Features	Barrier Resin		
	Biodegradable		
	General Purpose		
	Heat Sealable		
	Renewable Resource Content		
	Sealable High Barrier PVdC Coated		
Uses	Film		
	General Purpose		
	Packaging		
Appearance	White		
Forms	Film		
Films	Nominal Value	Unit	Test Method
Seal Initiation Temperature ¹ (24 µm)	43.3 to 98.9	°C	
Oxygen Transmission Rate (Wet) (24°C, 24 µm, 0.0% RH)	2.95	cm ³ /m ² /24 hr	ASTM F1927
Water Vapor Transmission Rate (24 µm, 38°C, 90% RH)	0.26	g · mm/m ² /atm/24 hr	ASTM E96
Film Gauge	23.6	µm	Internal Method
Yield (23.6 µm)	27.7	m ² /kg	Internal Method
NOTE			

1. 0.5 sec dwell, 10 psi

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

