

ALCOM® PP 620/1 WT1034-05LB

Polypropylene
ALBIS PLASTIC GmbH

Message:

ALCOM® PP 620/1 WT1034-05LB is a Polypropylene product filled with 30% filler. It is available in Asia Pacific, Europe, or North America. Applications of ALCOM® PP 620/1 WT1034-05LB include automotive and lighting applications.

Characteristics include:

REACH Compliant

RoHS Compliant

General Information			
Filler / Reinforcement	Filler,30% Filler by Weight		
Features	High Reflectivity		
Uses	Automotive Applications		
	Lighting Applications		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Opaque		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	25.0	cm³/10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3100	MPa	ISO 527-2
Tensile Strain (Break)	25	%	ISO 527-2
Flexural Stress	55.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	40	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	79.0	°C	ISO 75-2/A
Vicat Softening Temperature	101	°C	ISO 306/B50
Additional Information	Nominal Value	Unit	Test Method
Tristimulus Value			
Y10 of Reflection	92	%	DIN 5033
Y10 of Transmittance : 500.0 µm	0.40	%	ISO 13468
Injection	Nominal Value	Unit	Test Method
Drying Temperature			
Circulation Dryer	80.0 to 100	°C	
Desiccant Dryer	80.0 to 100	°C	

Drying Time		
Circulation Dryer	2.0 to 4.0	hr
Desiccant Dryer	2.0 to 3.0	hr
Processing (Melt) Temp	200 to 270	°C
Mold Temperature	20.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

