

LNP™ THERMOCOMP™ RFZ349XC

compound

Polyamide 66

SABIC Innovative Plastics

Message:

LNP THERMOCOMP RFZ349XC is a compound based on Nylon 66 resin containing Glass Fiber, Milled Glass. Added features of this material include: Flame Retardant.

Also known as: LNP* THERMOCOMP* Compound RF-1007 FR MG LEX

Product reorder name: RFZ349XC

General Information			
Filler / Reinforcement	Grinding Glass/Fiberglass		
Features	Flame retardancy		
Physical	Nominal Value	Unit	Test Method
Density	1.66	g/cm ³	ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.40	%	ASTM D955
Transverse flow: 24 hours	1.2	%	ASTM D955
Vertical flow direction: 24 hours	1.2	%	ISO 294-4
Flow direction: 24 hours	0.39	%	ISO 294-4
Water Absorption			
24 hr, 50% RH	0.20	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.43	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	11000	MPa	ASTM D638
--	11400	MPa	ISO 527-2/1
Tensile Strength			
Fracture	125	MPa	ASTM D638
Fracture	85.0	MPa	ISO 527-2
Tensile Elongation			
Fracture	2.3	%	ASTM D638
Fracture	3.2	%	ISO 527-2
Flexural Modulus			
--	7170	MPa	ASTM D790
--	9000	MPa	ISO 178
Flexural Strength			
--	179	MPa	ASTM D790
--	197	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			
23°C	64	J/m	ASTM D256
23°C ²	7.7	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	590	J/m	ASTM D4812
23°C ³	39	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	7.00	J	ASTM D3763
--	2.30	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	237	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	235	°C	ISO 75-2/Af
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

