

# PREMIER™ A230-FRHF

Polycarbonate + ABS

Chomerics, div. of Parker Hannifin Corp.

## Message:

PREMIER™ is the world's first and most versatile commercially available conductive thermoplastic for real world EMI shielding solutions. It is a blend of PC/ABS thermoplastic polymer alloys and conductive fillers engineered for stable electrical, mechanical, and physical performance. The conductive filler technology utilizes nickel plated carbon (Ni-C) fibers as the base filler. In the case of higher shielding versions, Nickel-Graphite (Ni-C) powder is blended with the fiber base to deliver enhanced performance.

General Information			
Filler / Reinforcement	Nickel-Coated Carbon Fiber		
Features	Electrically Conductive		
	Electromagnetic Shielding (EMI)		
	Good Corrosion Resistance		
	Halogen Free		
	High Tensile Strength		
	Low Density		
	Non-Corrosive		
	Recyclable Material		
Uses	Automotive Applications		
	Consumer Applications		
	Electrical/Electronic Applications		
	Industrial Applications		
	Military Applications		
	Telecommunications		
Agency Ratings	EU Unspecified Rating		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm <sup>3</sup>	ASTM D3763
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6700	MPa	ASTM D638
Tensile Strength (Break)	71.0	MPa	ASTM D638
Tensile Elongation (Break)	1.2	%	ASTM D638
Flexural Modulus	6300	MPa	ASTM D790
Flexural Strength	95.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D412

Unnotched Izod Impact	180	J/m	ASTM D412
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	100	°C	ASTM D648
CLTE - Flow	3.0E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.59	W/m/K	ASTM D5470
RTI Elec	70.0	°C	UL 746
RTI Imp	70.0	°C	UL 746
RTI Str	70.0	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	0.60	ohms	
Volume Resistivity	0.060	ohms · cm	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

