

Forprene® 6NM901D40

Thermoplastic Vulcanizate

SO.F.TER. SPA

Message:

Forprene® 6NM901D40 is a Thermoplastic Vulcanizate (TPV) material. It is available in Europe, Latin America, or North America for injection molding.

Primary attribute of Forprene® 6NM901D40: REACH Compliant.

Typical applications include:

Automotive

Engineering/Industrial Parts

Industrial Applications

General Information			
Uses	Automotive Applications		
	Grommets		
	Industrial Applications		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.950	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	41		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (100% Strain)	8.10	MPa	ASTM D412
Tensile Strength ²	17.0	MPa	ASTM D412
Tensile Elongation ³ (Break)	630	%	ASTM D412
Tear Strength ⁴	65.0	kN/m	ASTM D624
Compression Set ⁵ (70°C, 22 hr)	61	%	ASTM D395B
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Rear Temperature	150	°C	
Middle Temperature	160	°C	
Front Temperature	170	°C	
Nozzle Temperature	175	°C	
Mold Temperature	20.0 to 40.0	°C	
NOTE			
1.	Die C		
2.	Die C		
3.	Die C		
4.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

