

Bergamid™ A70 MI40 H NC017

Polyamide 66
PolyOne Corporation

Message:
Bergamid™A70 MI40 H NC017 is a polyamide 66 (nylon 66) product that contains a mineral filler. It can be processed by injection molding and is available in the Asia-Pacific region.

General Information			
Filler / Reinforcement	Mineral filler		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.48	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40 - 0.90	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	65.0	MPa	ASTM D638
Flexural Modulus ²	5000	MPa	ASTM D790
Flexural Strength ³	130	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	35	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	90.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	4.0 - 6.0	hr	
Rear Temperature	260 - 280	°C	
Middle Temperature	260 - 280	°C	
Front Temperature	260 - 280	°C	
Mold Temperature	65.0 - 85.0	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			
1.	5.0 mm/min		
2.	1.3 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

