

POLYTROPE® STR 2030REU-01 NATURAL

Enhanced TPO Polyolefin

A. Schulman Inc.

Message:

POLYTROPE STR 2030REU is a flame retardant TPO resin which is UL 94 V-0 and 5VA compliant, RoHS compliant, and specifically designed to provide high melt strength for extrusion, and thermoforming processes. It is non-blooming, and provides balanced impact resistance with stiffness, making it especially suitable for panel and closure applications requiring flame retarding properties. It can be extruded in smooth or textured surfaces, or co-extruded with a POLYTROPE STR enhanced polyolefin cap resin to further customize its' durability, appearance, or feel for interior and exterior applications. The capability of POLYTROPE STR 2030REU to provide an exceptionally smooth surface in extrusion and thermoforming makes it well suited to lamination processes with decorative films. It is also easily colored and is paintable by standard TPO paint systems.

General Information			
Features	Flame Retardant		
	Good Melt Strength		
	Good Weather Resistance		
	Low CLTE		
	Paintable		
	Recyclable Material		
Agency Ratings	UL 94 2		
Forms	Pellets		
Processing Method	Coextrusion		
	Extrusion		
	Profile Extrusion		
	Sheet Extrusion		
	Thermoforming		
Physical	Nominal Value	Unit	Test Method
Specific Gravity ¹	1.31	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.80	g/10 min	ISO 1133
Molding Shrinkage (23°C, 24 hr, 3.18 mm)	0.80 to 1.2	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ² (Yield, 23°C)	19.0	MPa	ISO 527-2
Tensile Strain ³ (Break, 233°C)	430	%	ISO 527-2
Flexural Modulus - Chord ⁴ (23°C)	1930	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact - Flow			ASTM D256
-30°C, 3.18 mm, Injection Molded	32	J/m	
23°C, 3.18 mm, Injection Molded	430	J/m	
Instrumented Dart Impact (-9°C, Total Energy, Ductile Failure)	35.0	J	ASTM D3763

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	90.6	°C	ISO 75-2/Bf
CLTE - Flow (-30 to 100°C)	5.4E-5	cm/cm/°C	ASTM E831
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
3.18 mm, All Colors	HB		
	V-0		
1.59 mm, All Colors	5VA		
Optical	Nominal Value		Test Method
Gardner Gloss (60°, 3180 µm, Thermoformed, Smooth)	20 to 40		ISO 2813
Additional Information	Nominal Value	Unit	Test Method
Heat Sag - 8 inch span, two point support (149°C, 3.20 mm)	0.00	mm	ASTM D3769
NOTE			
1.	Method A		
2.	Type 1, 50 mm/min		
3.	Type 1, 50 mm/min		
4.	Type 1A, 2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

