

Sangel® WAF100

Styrene Acrylonitrile

Unigel Plásticos

Message:

SAN Resin (Styrene / Acrylonitrile copolymer), very high-flow grade, high chemical resistance, good rate stiffness/impact, high gloss and tranparence

Applications:

Household appliances

Kitchenware

Cosmetic packaging

General Information			
Features	Good Chemical Resistance		
	Good Impact Resistance		
	Good Stiffness		
	High Clarity		
	High Flow		
	High Gloss		
Uses	Appliances		
	Cosmetic Packaging		
	Household Goods		
	Kitchenware		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.08	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	16	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	64.7	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	3000	MPa	ASTM D790
Flexural Strength	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	15	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	100	°C	ASTM D1525 ¹
Optical	Nominal Value	Unit	Test Method
Transmittance (0.420 µm)	84.0	%	ASTM D1003
Injection	Nominal Value	Unit	
Drying Temperature	85.0	°C	
Drying Time	4.0	hr	

Rear Temperature	200 to 220	°C
Middle Temperature	220 to 240	°C
Front Temperature	225 to 245	°C
Nozzle Temperature	225 to 245	°C
Mold Temperature	40.0 to 80.0	°C

NOTE

1. Rate B (120°C/h), Loading 1 (10 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

