

ResMart Repro HIPS Black

High Impact Polystyrene

ResMart

Message:

General Purpose Reprocessed Impact Polystyrene Black

General Information			
Recycled Content	Yes		
Features	General		
Uses	General		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	4.0 - 9.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	98		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	30.3	MPa	ASTM D638
Flexural Modulus	2070	MPa	ASTM D790
Flexural Strength	42.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	77.8	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	73.9	°C	
Drying Time - Desiccant Dryer	4.0	hr	
Suggested Max Moisture	0.10	%	
Processing (Melt) Temp	191 - 246	°C	
Mold Temperature	51.7 - 68.3	°C	
Injection Pressure	68.9 - 96.5	MPa	
Injection instructions			
Dew Point: 0°F			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

