

4TECH® 9S22110

Polyphenylene
4Plas

Message:

4TECH 9S22110 is a Standard Flow 10% Glass Fibre Reinforced PPO

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Moisture Content	< 2000	ppm	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4750	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	70.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	7.0	kJ/m ²	ISO 180/1A
23°C	9.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	115	°C	ISO 75-2/A
Vicat Softening Temperature	125	°C	ISO 306/B
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.750 mm	HB		UL 94
1.60 mm	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 90.0	°C	
Drying Time	2.0 - 3.0	hr	
Suggested Max Moisture	0.020	%	
Processing (Melt) Temp	270 - 300	°C	
Mold Temperature	80.0 - 120	°C	
Injection Rate	Slow-Moderate		
Holding Pressure	60.0 - 120	MPa	
Screw Speed	250	rpm	
Injection instructions			

Feed Throat Temperature: 60 - 80 °CBack Pressure: Low

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

