

XANTAR® SF 2230

Polycarbonate
Mitsubishi Engineering-Plastics Corp

Message:
30% Glass Reinforced, Structural Foam

General Information			
UL YellowCard	E340159-100746677		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
	Foamable		
Uses	Structural Foam		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density			ISO 1183
-- ¹	1.11	g/cm ³	
--	1.43	g/cm ³	
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	4.00	cm ³ /10min	ISO 1133
Water Absorption (Saturation, 23°C)	0.30	%	ISO 62
Limiting Viscosity Number	48.0	cm ³ /g	ISO 1628-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6500	MPa	ISO 527-2
Tensile Stress (Break)	70.0	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	137	°C	ISO 75-2/A
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE - Flow	1.0E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Relative Permittivity			IEC 60250
100 Hz	3.30		
1 MHz	3.30		
Dissipation Factor			IEC 60250
100 Hz	8.0E-4		

1 MHz	9.0E-3		
Flammability	Nominal Value	Unit	Test Method
	V-0		
Flammability Classification (4.80 mm)	5VA		IEC 60695-11-10, -20
Oxygen Index	36	%	ISO 4589-2
NOTE			
1.	Foamed		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT