

# Generic ASA+Nylon

Acrylonitrile Styrene Acrylate + Nylon

Generic

## Message:

This data represents typical values that have been calculated from all products classified as: Generic ASA+Nylon  
This information is provided for comparative purposes only.

General Information			
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1200 to 3400	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	34.0 to 57.0	MPa	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0 to 21	kJ/m <sup>2</sup>	ISO 179
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	105 to 205	°C	ISO 306

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

